

DOPORUČENÁ ZÁMĚNA KOMPOZITU A OCELI

Kompozitní výztuž	Váha kompozitu	Ocelová výztuž	Váha oceli	Kompozit je x krát lehčí
Průměr mm	kg / m	Průměr mm	kg / m	
ROXOR 4	0,026	6	0,22	8,5
ROXOR 6	0,055	8	0,40	7,3
ROXOR 8	0,098	10	0,62	6,3
ROXOR 8	0,098	12	0,89	9,1
ROXOR 10	0,153	14	1,21	7,9
ROXOR 12	0,185	16	1,58	8,5
ROXOR 14	0,221	18	2,00	9,0
ROXOR 16	0,300	20	2,47	8,2

Kompozitní síť	Hmotnost m2	Ocelová kari síť	Hmotnost m2	Kompozit je x krát lehčí
Průměr / oko		Průměr / oko		
3/10x10	0,240	4/10x10	1,980	8,3
	0,240	4/15x15	1,353	5,6
	0,240	4/20x20	0,990	4,1
	0,240	5/15x15	2,105	8,8
	0,240	5/20x20	1,540	6,4
3/15x15	0,170	4/15x15	1,353	8,0
	0,170	4/20x20	0,990	5,8
	0,170	5/15x15	2,105	12,4
	0,170	5/20x20	1,540	9,1
3/20x20	0,120	4/20x20	0,990	8,3
4/10x10	0,485	5/10x10	3,080	6,4
	0,485	5/15x15	2,105	4,3
	0,485	5/20x20	1,540	3,2
	0,485	6/10x10	4,440	9,2
	0,485	6/15x15	3,033	6,3
	0,485	8/15x15	5,398	11,1
	0,485	8/20x20	3,950	8,1
4/15x15	0,360	4/10x10	1,980	5,5
	0,360	5/15x15	2,105	5,8
	0,360	5/20x20	1,540	4,3
4/20x20	0,245	4/15x15	1,353	5,5
	0,245	5/20x20	1,540	6,3
6/10x10	1,000	8/10x10	7,900	7,9
	1,000	8/15x15	5,398	5,4
	1,000	8/20x20	3,950	4,0
6/15x15	0,700	8/15x15	5,398	7,7
	0,700	8/20x20	3,950	5,6
6/20x20	0,500	6/15x15	3,033	6,1
	0,500	8/20x20	3,950	7,9